

Model: LINZ ANTRACITA 59,6X150(A)

Codes: 100303835

Water absorption: BIII - Cladding Tile ( $10.0\% < w_a \leq 20.0\%$ )

Finish: Glazed / Standard

Tone variations: V3

Rectified: Yes



## DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

|                             |             |          |
|-----------------------------|-------------|----------|
| Thickness                   | 10.5 mm     | +/-5%*   |
| Width                       | 596 mm      |          |
| Length                      | 1500 mm     |          |
| Length and width deviation  | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation        | Below 0.15% | +/-0.3%* |
| Surface flatness deviation  | Below 0.15% | +/-0.4%* |

\*ISO-13006:2018 UNE-EN 14411:2016

## FEATURES

 Natural-looking, non-glossy surface finish.

 Name given to the finish of those tiles dimensionally improved after the firing process.

 Wall installation

## MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-9-11

|                    |                       |                          |
|--------------------|-----------------------|--------------------------|
| Breaking strength  | >600 N                | >600 N*                  |
| Modulus of rupture | >15 N/mm <sup>2</sup> | >=12 N/mm <sup>2</sup> * |
| Crazing resistance | PASS                  |                          |

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14

|                     |                                                                                                            |         |
|---------------------|------------------------------------------------------------------------------------------------------------|---------|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance    | Class 5. Easy cleaning with water                                                                          | 3 Min.* |

\*ISO-13006:2018 UNE-EN 14411:2016

## ANTI-SLIP VALUE

Reference standards: EN 16165 (Annex A, B, C) - ANSI A326.3 - AS 4586

|                                        |       |  |
|----------------------------------------|-------|--|
| Dynamic coefficient of friction (dcof) | >0,42 |  |
|----------------------------------------|-------|--|

\*ISO-13006:2018 UNE 14411:2016 ANSI 137.1 AS 4662

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## DETERMINATION OF LIGHT REFLECTANCE VALUE (LRV) UNE-EN ISO 10545-18

Determination of light reflectance value (Irv)

19.32

\*ISO-13006:2018 UNE-EN 14411:2016

## PACKING

Sales units per box

2.681924 M2/BOX

Sales units per pallet

53.638477 M2/PAL

Sales units per unit

0.893975 M2/PIECE

## SCOPE OF USE

Technical code-1

1 - Use on walls

### System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.