

Model: PARK GRIS L 25X44,3(A)

Codes: 100322666

Water absorption: BIII - Cladding Tile ( $10.0\% < w_a \leq 20.0\%$ )

Finish: Glazed / Standard

Tone variations: V3

Rectified: Not



## DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

|                             |             |          |
|-----------------------------|-------------|----------|
| Thickness                   | 7 mm        | +/-5%*   |
| Width                       | 248.4 mm    |          |
| Length                      | 443 mm      |          |
| Length and width deviation  | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation        | Below 0.15% | +/-0.3%* |
| Surface flatness deviation  | Below 0.15% | +/-0.4%* |

\*ISO-13006:2018 UNE-EN 14411:2016

## FEATURES



Natural-looking, non-glossy surface finish.



Wall installation

## MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-9-11

|                    |                      |                          |
|--------------------|----------------------|--------------------------|
| Breaking strength  | 850 N                | >600 N*                  |
| Modulus of rupture | 27 N/mm <sup>2</sup> | >=12 N/mm <sup>2</sup> * |
| Crazing resistance | PASS                 |                          |

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14

|                     |                                                                                                            |         |
|---------------------|------------------------------------------------------------------------------------------------------------|---------|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance    | Class 5. Easy cleaning with water                                                                          | 3 Min.* |

\*ISO-13006:2018 UNE-EN 14411:2016

## DETERMINATION OF LIGHT REFLECTANCE VALUE (LRV)

 UNE-EN ISO 10545-18

|                                                |       |  |
|------------------------------------------------|-------|--|
| Determination of light reflectance value (Irv) | 49.69 |  |
|------------------------------------------------|-------|--|

\*ISO-13006:2018 UNE-EN 14411:2016

## PACKING

|                        |                   |  |
|------------------------|-------------------|--|
| Sales units per box    | 1.661258 M2/BOX   |  |
| Sales units per pallet | 112.965568 M2/PAL |  |
| Sales units per unit   | 0.110751 M2/PIECE |  |

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

| SCOPE OF USE     |                  |  |
|------------------|------------------|--|
| Technical code-1 | 1 - Use on walls |  |

System Certification

