

Model: BLUE ROMA POL.(6) 59,6X120(A)

Codes: 100338789

Absorption: Bla - Porcelain tile (wa <= 0.1%)

Finish: Unglazed / Standard

Tone variations: V3

Rectified: Yes



DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

Length	1200 mm	
Thickness	6 mm	
Width	596 mm	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

*ISO-13006:2015 UNE-EN 14411:2017

FEATURES

- | | |
|--|--|
| <p> Tile with a high degree of compaction, uniform in appearance and with a lower percentage of glazing in the composition.</p> <p> General deshaded design with a degree of color and appearance variation.</p> <p> Name given to the finish of those tiles dimensionally improved after the firing process.</p> <p> Ceramic tiles that can be installed outdoors</p> | <p> An exclusive large-format floor tile which has been thought up for those surfaces that look for an optical continuity and greater spaciousness.</p> <p> Moderate variation. The color intensity of each piece may vary significantly, although the colors present in one tile will be representative of the colors to be expected in the rest of the tiles</p> <p> Installation on floor</p> |
|--|--|

MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-9-11

Breaking strenght	1435.7 N	UNE-EN ISO 10545-4:2019*
Modulus of rupture	51.8 N/mm2	UNE-EN ISO 10545-4:2019*
Crack resistance	RESISTE 3 CICLOS	
Resistance to thermal shock	RESISTE	

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
Resistance to thermal shock	RESISTE	

*ISO-13006:2018 UNE-EN 14411:2016

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

ANTI-SLIP VALUE

Reference standards: EN 16165 (Annex A, B, C) - ANSI A326.3 - AS 4586

Slip resistance (wet pendulum) irhd 55

CL0

UNE EN 16165 Anexo C*

Slip resistance (pendulum-dry)

>40*

*ISO-13006:2018 UNE 14411:2016 ANSI 137.1 AS 4662

PACKING

Sales units per box

2.145616 M2/BOX

Sales units per pallet

64.368474 M2/PAL

Sales units per unit

0.715205 M2/PIECE

SCOPE OF USE

Technical code-1

3 - Light traffic with no direct access to the outside

Technical code-2

0 - No additional requirements

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.