

Model: FIUME LIMESTONE MARFIL 59,6X150(A)

Codes: 100381301

Water absorption: BIII - Cladding Tile ($10.0\% < w_a \leq 20.0\%$)

Finish: Glazed

Tone variations: V3

Rectified: Yes



DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Thickness	12.5 mm	+/-5%*
Width	596 mm	
Length	1500 mm	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

*ISO-13006:2018 UNE-EN 14411:2016

FEATURES



General deshaded design with a degree of color and appearance variation.



Moderate variation. The color intensity of each piece may vary significantly, although the colors present in one tile will be representative of the colors to be expected in the rest of the tiles



Name given to the finish of those tiles dimensionally improved after the firing process.



Finish with clearly defined protrusions that give the surface a feeling of volume.

MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-9-11

Crazing resistance	PASS	
--------------------	------	--

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

UNE-EN ISO 10545-13-14

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*

*ISO-13006:2018 UNE-EN 14411:2016

PACKING

Sales units per box	2.681924 M2/BOX	
Sales units per pallet	48.274629 M2/PAL	
Sales units per unit	0.893975 M2/PIECE	

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.