

Model: ARIA WHITE NAT.03 120X270(6)(A)

Codes: 100332180

Absorption: Bla - Porcelain tile (wa <= 0.1%)

Finish: Standard

Tone variations: V2

Rectified: Yes



DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Length	2700 mm	
Thickness	6 mm	
Width	1200 mm	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

*ISO-13006:2015 UNE-EN 14411:2017

FEATURES

- Nature
- General deshed design with a degree of color and appearance variation.
- Slight variation. Clearly perceptible differences in texture and/or design, but with similar colors
- Name given to the finish of those tiles dimensionally improved after the firing process.
- Wall installation
- Ceramic tiles that can be installed outdoors

MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-9-11

Breaking strenght	>1100 N	
Modulus of rupture	> 45 N/mm2	
Abrasion resistance	<140 mm3	

*ISO-13006:2018 UNE-EN 14411:2016

HYGIENIC FEATURES

UNE-EN ISO 10545-13-14

Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
Flammability	A1	

*ISO-13006:2018 UNE-EN 14411:2016

ANTI-SLIP VALUE

Reference standards: EN 16165 (Annex A, B, C) - ANSI A326.3 - AS 4586

Slip resistance (wet pendulum) irhd 55 CL1

*ISO-13006:2018 UNE 14411:2016 ANSI 137.1 AS 4662

System Certification



ADDITIONAL NOTES

*COMPOSITION WITH CONTINUITY, MAXIMUM DEVIATION IN GRAPHIC CONTINUITY BETWEEN PIECES 1.5 CM

DETERMINATION OF LIGHT REFLECTANCE VALUE (LRV) UNE-EN ISO 10545-18

Determination of light reflectance value (Irv)

74

*ISO-13006:2018 UNE-EN 14411:2016

PACKING

Sales units per box

3.240441 M2/BOX

Sales units per pallet

71.289695 M2/PAL

Sales units per unit

3.240441 M2/PIECE

SCOPE OF USE

Technical code-1

1 - Coating

Technical code-2

0 - No additional requirements

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.