

Model: CALACATTA GOLD POL.01 120X270(6)(A)

Codes: 100332439

Absorption: Bla - Porcelain tile (wa <= 0.1%)

Finish: Unglazed / Standard

Tone variations: V3

Rectified: Yes



## DIMENSIONAL FEATURES

 UNE-EN ISO 10545-2

|                             |             |          |
|-----------------------------|-------------|----------|
| Length                      | 2700 mm     |          |
| Thickness                   | 6 mm        |          |
| Width                       | 1200 mm     |          |
| Length and width deviation  | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation        | Below 0.15% | +/-0.3%* |
| Surface flatness deviation  | Below 0.15% | +/-0.4%* |

\*ISO-13006:2015 UNE-EN 14411:2017

## FEATURES

- Tile with a high degree of compaction, uniform in appearance and with a lower percentage of glazing in the composition.
- General deshaded design with a degree of color and appearance variation.
- Name given to the finish of those tiles dimensionally improved after the firing process.
- Ceramic tiles that can be installed outdoors
- Infinite horizontal graphic continuity
- Moderate variation. The color intensity of each piece may vary significantly, although the colors present in one tile will be representative of the colors to be expected in the rest of the tiles
- Wall installation

## MECHANICAL FEATURES

 UNE-EN ISO 10545-4-6-7-9-11

|                     |            |    |
|---------------------|------------|----|
| Breaking strenght   | >1100 N    | -* |
| Modulus of rupture  | > 45 N/mm2 |    |
| Abrasion resistance | < 140      |    |

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES

 UNE-EN ISO 10545-13-14

|                     |                                                                                                            |         |
|---------------------|------------------------------------------------------------------------------------------------------------|---------|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance    | Class 5. Easy cleaning with water                                                                          | 3 Min.* |
| Flammability        | A1                                                                                                         |         |

\*ISO-13006:2018 UNE-EN 14411:2016

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## ANTI-SLIP VALUE

Reference standards: EN 16165 (Annex A, B, C) - ANSI A326.3 - AS 4586

|                                        |                        |  |
|----------------------------------------|------------------------|--|
| Dynamic coefficient of friction (dcof) | < 0.42                 |  |
| Slip resistance (wet pendulum) irhd 55 | CL0                    |  |
| Pendulum test value (ptv) irhd 96      | DRY>36-LOW_WET<25-HIGH |  |
| Slip resistance (pendulum-dry)         | >40                    |  |

\*ISO-13006:2018 UNE 14411:2016 ANSI 137.1 AS 4662

## ADDITIONAL NOTES

\*COMPOSITION WITH CONTINUITY, MAXIMUM DEVIATION IN GRAPHIC CONTINUITY BETWEEN PIECES 1.5 CM

## DETERMINATION OF LIGHT REFLECTANCE VALUE (LRV)

UNE-EN ISO 10545-18

|                                                |    |  |
|------------------------------------------------|----|--|
| Determination of light reflectance value (Irv) | 64 |  |
|------------------------------------------------|----|--|

\*ISO-13006:2018 UNE-EN 14411:2016

## PACKING

|                        |                   |  |
|------------------------|-------------------|--|
| Sales units per box    | 3.240441 M2/BOX   |  |
| Sales units per pallet | 71.289695 M2/PAL  |  |
| Sales units per unit   | 3.240441 M2/PIECE |  |

## SCOPE OF USE

|                  |                                |  |
|------------------|--------------------------------|--|
| Technical code-1 | 1 - Coating                    |  |
| Technical code-2 | 0 - No additional requirements |  |

System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.